CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 11/11/2019

Lab ID	:	**CP-2019-12-07-16**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of CC Road at NMH Layout 5th Cross in Bagalagunte Ward No.14.
Agency	:	Sri.K.S Ramesh, #127, 3rd Cross, Ramaiah Layout, Nagasandra Post, Bangalore-73.
Customer's Reference	:	EE/DD/WO/403/19-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-11-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/11/2019	11/11/2019	151.24 X 150.77 X 151.52	22802	8.784	430.3	18.9	18.5
2	Drain Bottom Slab Concrete	M20	04/11/2019	11/11/2019	151.05 X 151.12 X 149.42	22827	8.106	419.3	18.4	
3	Drain Bottom Slab Concrete	M20	04/11/2019	11/11/2019	150.73 X 151.12 X 149.35	22779	8.340	417.3	18.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 02/12/2019

Lab ID	:	**CP-2019-12-07-16**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of CC Road at NMH Layout 5th Cross in Bagalagunte Ward No.14.
Agency	:	Sri.K.S Ramesh, #127, 3rd Cross, Ramaiah Layout, Nagasandra Post, Bangalore-73.
Customer's Reference	:	EE/DD/WO/403/19-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-11-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/11/2019	02/12/2019	150.95 X 151.37 X 150.73	22849	**8.305**	542.5	23.7	23.5
2	Drain Bottom Slab Concrete	M20	04/11/2019	02/12/2019	150.49 X 149.95 X 151.07	22566	**8.060**	518.8	23.0	
3	Drain Bottom Slab Concrete	M20	04/11/2019	02/12/2019	150.34 X 150.39 X 150.23	22610	**8.602**	535.7	23.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 11/11/2019

Lab ID	:	CP-2019-12-07-16
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of CC Road at NMH Layout 5th Cross in Bagalagunte Ward No.14.
Agency	:	Sri.K.S Ramesh, #127, 3rd Cross, Ramaiah Layout, Nagasandra Post, Bangalore-73.
Customer's Reference	:	EE/DD/WO/403/19-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-11-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/11/2019	11/11/2019	151.59 X 149.32 X 149.71	22636	8.784	415.9	18.4	18.4
2	Drain Bottom Slab Concrete	M20	04/11/2019	11/11/2019	149.27 X 149.51 X 151.14	22318	8.106	418.9	18.8	
3	Drain Bottom Slab Concrete	M20	04/11/2019	11/11/2019	150.61 X 151.21 X 150.44	22774	8.340	412.7	18.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
(ಬೆಂಗಳೂರು)

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig..... Date.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 02/12/2019

Lab ID	:	**CP-2019-12-07-16**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of CC Road at NMH Layout 5th Cross in Bagalagunte Ward No.14.
Agency	:	Sri.K.S Ramesh, #127, 3rd Cross, Ramaiah Layout, Nagasandra Post, Bangalore-73.
Customer's Reference	:	EE/DD/WO/403/19-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-11-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	04/11/2019	02/12/2019	149.61 X 150.15 X 149.95	22464	8.305	517.7	23.0	22.9
2	Drain Bottom Slab Concrete	M20	04/11/2019	02/12/2019	150.81 X 151.27 X 151.88	22813	8.060	502.3	22.0	
3	Drain Bottom Slab Concrete	M20	04/11/2019	02/12/2019	149.71 X 150.51 X 150.80	22533	8.602	530.6	23.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2019-12-07-16** **Date: 12/11/2019**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of CC Road at NMH Layout 5th Cross in Bagalagunte Ward No.14.

Agency : Sri.K.S Ramesh, #127, 3rd Cross, Ramaiah Layout, Nagasandra Post, Bangalore-73.

Customer's Reference : EE/DD/WO/403/19-20

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-11-19

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/11/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	05/11/2019	12/11/2019	149.33 X 149.55 X 150.85	22332	**8.784**	415.5	18.6	18.7
2	Drain Side Wall Concrete	M20	05/11/2019	12/11/2019	149.08 X 150.66 X 149.51	22460	**8.106**	425.2	18.9	
3	Drain Side Wall Concrete	M20	05/11/2019	12/11/2019	149.47 X 149.10 X 149.68	22286	**8.340**	414.5	18.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ದಾಸರಹಳ್ಳಿ ಉಪ-ವಿಭಾಗ
ಬಾಗಲಗುಂಟೆ, ಬಿಬಿಎಂಪಿ
ಬೆಂಗಳೂರು

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 03/12/2019

Lab ID	:	**CP-2019-12-07-16**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of CC Road at NMH Layout 5th Cross in Bagalagunte Ward No.14.
Agency	:	Sri.K.S Ramesh, #127, 3rd Cross, Ramaiah Layout, Nagasandra Post, Bangalore-73.
Customer's Reference	:	EE/DD/WO/403/19-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	07-11-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	03/12/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	05/11/2019	03/12/2019	150.14 X 149.78 X 150.91	22489	**8.305**	526.4	23.4	23.1
2	Drain Side Wall Concrete	M20	05/11/2019	03/12/2019	151.65 X 149.70 X 151.17	22702	**8.060**	511.2	22.5	
3	Drain Side Wall Concrete	M20	05/11/2019	03/12/2019	149.26 X 150.57 X 149.19	22474	**8.602**	527.2	23.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner